

IN THE CLAIMS

Please amend the claims as follows:

1. (original) A color-mixing lighting system (1) comprising:
a light-emitting diode (6, 7) emitting first visible light
having a first peak wavelength in a first spectral range,
a fluorescent material (8, 9) converting a portion of the
first visible light into second visible light having a second peak
wavelength in a second spectral range,
the second visible light having a full width at half maximum
(FWHM) of at least 50 nm.
2. (original) A color-mixing lighting system as claimed in
claim 1, characterized in that the second visible light is red
light, the second peak wavelength being in the range from 590 to
630 nm.
3. (original) A color-mixing lighting system as claimed in
claim 2, characterized in that the second peak wavelength is in the
range from 600 to 615 nm.
4. (currently amended) A color-mixing lighting system as claimed
in claim 1 ~~or 2~~, characterized in that the first visible light-

emitting diode (6) emits blue light, the first peak wavelength being in the range from 445 to 470 nm and the full-width at half maximum (FWHM) being in the range from 15 to 30 nm.

5. (currently amended) A color-mixing lighting system as claimed in claim 1-~~or~~2, characterized in that the lighting system comprises a further light-emitting diode (7) for emitting third visible light having a third peak wavelength in a third spectral range.

6. (original) A color-mixing lighting system as claimed in claim 4, characterized in that the further light-emitting diode (7) emits green light, the third peak wavelength being in the range from 510 to 550 nm and the full width at half maximum (FWHM) being in the range from 25 to 45 nm.

7. (currently amended) A color-mixing lighting system as claimed in claim 1-~~or~~2, characterized in that the fluorescent material (8) converts blue light into red light, the fluorescent material being selected from the group formed by SrS:Eu , $\text{Sr}_2\text{Si}_5\text{N}_8\text{:Eu}$, CaS:Eu , $\text{Ca}_2\text{Si}_5\text{N}_8\text{:Eu}$, $(\text{Sr}_{1-x}\text{Ca}_x)\text{S:Eu}$ and $(\text{Sr}_{1-x}\text{Ca}_x)_2\text{Si}_5\text{N}_8\text{:Eu}$ and ($x = 0.0-1.0$).

8. (currently amended) A color-mixing lighting system as claimed in claim 1-~~or~~2, characterized in that the lighting system comprises a further fluorescent material (9) converting a portion of the first visible light into third visible light having a third peak wavelength in a third spectral range with the third peak wavelength in the range from 510 to 550 nm and a FWHM of at least 40 nm.

9. (original) A color-mixing lighting system as claimed in claim 7, characterized in that the further fluorescent material (9) converts blue light into green light, the fluorescent material being selected from the group formed by $(\text{Ba}_{1-x}\text{Sr}_x)_2\text{SiO}_4:\text{Eu}$ ($x = 0-1$, preferably $x = 0.5$), $\text{SrGa}_2\text{S}_4:\text{Eu}$, $\text{Lu}_3\text{Al}_5\text{O}_{12}:\text{Ce}$ and $\text{SrSi}_2\text{N}_2\text{O}_2:\text{Eu}$.